



Your Single Source For Innovative
Architectural Concrete Solutions

June 2009

BOMANITE FLOOR COATING COEFFICIENT OF FRICTION DATA

BOMANITE FLOOR COATING	ASTM D-2047 READING
Bomanite Clear Cure	0.8
Bomanite Florthane SB	Equal to or greater than 0.5
Bomanite Florthane WB	Equal to or greater than 0.5
Bomanite Hydrocoat	0.6
Bomanite Interior Floor Finish	0.6
Bomanite Natural Beauty	0.6
Bomaseal I-18	0.7
Bomaseal I-27	0.9
Bomaseal VOC II	0.9