



Technical Bulletin and Application Guideline

Page: 1 of 1
November 2003

BOMANITE CON-CLEAN EXTRA-STRENGTH CONCRETE CLEANER

PRODUCT DESCRIPTION

Bomanite Con-Clean was developed to clean and remove surface minerals from concrete and similar masonry surfaces. Bomanite Con-Clean is especially useful for preparation of concrete prior to application of a sealer, such as BomaSeal I-18, BomaSeal VOC II, or Bomanite Hydrocoat. With proper dilution and application, Bomanite Con-Clean will not change the color or damage the concrete. Always test in an inconspicuous area before using Bomanite Con-Clean.

APPLICATION

Bomanite Con-Clean is a concentrate and must be diluted before use. Dilute one part of Bomanite Con-Clean with 20 parts of water (six ounces per gallon; one quart per five gallons). Apply with a low-pressure sprayer, allowing five minutes dwell time. Follow with pressure washing, rinse thoroughly and let dry. Scrubbing with a Nylo-grit brush before pressure washing will increase cleaning efficiency.

SPECIFICATIONS

| | |
|--------------------------------|--|
| COLOR | Red |
| ODOR..... | Mild |
| pH..... | 0.5 ± 0.2 |
| DILUTION RATE | 20:1 (6 ounces per gallon of water) |
| METHOD OF APPLICATION | Acid proof pump sprayer |
| COVERAGE | 4000 square feet per gallon |
| DETERGENT TYPE | Nonionic |
| SPECIFIC GRAVITY | 1.3 |
| DENSITY | 11.0 pounds per gallon |
| FLASH POINT..... | None (C.O.C. Method) |
| SURFACE TENSION | 29 dynes per cm (at 2 oz. per gallon dilution) |
| VOC CONTENT | Less than 1% |
| SOLUBILITY IN WATER | 100% (hard, soft and/or deionized water) |
| FREEZE/THAW STABILITY | Minimum 3 cycles (ASTM Test D-3209-82) |
| SHELF LIFE | Minimum 1 year from date of sale |
| CONTAINER SIZES AVAILABLE..... | 4 x 1 gallon jugs 5-gallon pail 55-gallon drum |

SPECIFICATION ASSISTANCE

Consult Bomanite for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

WARRANTY

This product is warranted to meet uniform quality standards within conventional manufacturing tolerances. Since no control is exercised over product use, no warranty or guarantee, expressed or implied, can be made to its use. Seller's and manufacturer's obligation under this warranty is limited to reimbursement of the purchase price of the portion of the product proven to be defective. The user assumes all risks and liability resulting from the use of this product.