

# Technical Bulletin and Application Guideline

Page: 1 of 1 June 2009

## **BOMASEAL STRIPPER**

### STRIPPER FOR SOLVENT AND WATER-BASED SEALERS

#### PRODUCT DESCRIPTION

Bomaseal Stripper was developed to provide a user-safe and environment-safe stripper for solvent-based seals and paints. Bomaseal Stripper contains no methylene chloride, is not flammable and is without the other problems associated with petroleum solvents. Bomaseal Stripper is safe to use on all masonry surfaces such as cement, quarry tile, ceramic tile, terrazzo or other masonry surfaces. It can be applied to horizontal surfaces or used in a dip tank.

#### **APPLICATION**

Bomaseal Stripper is water dispersible; however, it is most effective when used as is. Apply Bomaseal Stripper using a mop or sprayer. Work small areas at a time. Do not walk in areas where Bomaseal Stripper is on the floor, as it is slippery underfoot. Allow 15 minutes dwell time, then scrape or scrub with a floor buffer and a Zim Grit brush. Pick up or vacuum solution, then scrub with Bomanite Concrete Degreaser diluted eight ounces per gallon of water, followed by thorough rinsing. Allow floor to dry before applying seal or finish.

#### **SPECIFICATIONS**

COLOR:	. Lt. straw
ODOR:	. Sweet, citrus
FLASH POINT:	. 140 °F
DILUTION RATE:	. Ready to use
METHOD OF APPLICATION:	. Solvent proof pump sprayer, mop
COVERAGE:	
DWELL TIME:	. 15 to 60 minutes or more, depending on type and amount of
	coating to be stripped.
BIODEGRADABLE:	
pH:	. 8 + 0.5
DETERGENT TYPE:	. Nonionic
SPECIFIC GRAVITY:	. 0.97
DENSITY:	. 8.1 pounds per gallon
SOLUBILITY IN WATER:	. Less than 1% (hard, soft and/or deionized water)
SHELF LIFE:	. Minimum 1 year from date of sale
FREEZE/THAW STABILITY:	. Minimum 3 cycles (A.S.T.M. Test D-3209-82)
CONTAINER SIZES:	. 5-gallon pail
	55-gallon drum

#### **SPECIFICATION ASSISTANCE**

Consult Bomanite for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

#### **WARRANTY**

This product is warranted to meet uniform quality standards within conventional manufacturing tolerances. Since no control is exercised over product use, no warranty or guarantee, expressed or implied, can be made to its use. Seller's and manufacturer's obligation under this warranty is limited to reimbursement of the purchase price of the portion of the product proven to be defective. The user assumes all risks and liability resulting from the use of this product.